

S.A.M. Adhesive

SELF-ADHERING
MEMBRANE ADHESIVE

 **COMMERCIAL**



S.A.M. Adhesive

SELF-ADHERING MEMBRANE ADHESIVE

STOCK# 1850032, 1850034

SIZE: 17 L pail (4.49 gal), 3.78 L (1 gal)

PALLET SIZE: 122 cm x 102 cm

(48 in x 40 in)

QUANTITY PER PALLET:

17 L Pail (4.49 gal) - 36

3.5 L Pail (1 gal) - 90 Boxes

(each containing 2 pails)

COLOUR: Gold

COVERAGE: 3 to 6 m²/L

DRYING TIME: 60 Minutes

Note: All reported values are nominal.

IKO S.A.M. Adhesive is an outstanding quick drying product for self-adhering membranes. Let S.A.M. Adhesive go to work for your next commercial building project.

- EXCELLENT ADHESION
- VERSATILE

Multi-Use

IKO S.A.M Adhesive is a surface conditioner where asphaltic self-adhesive membranes are applied. It is suitable for use on most substrates including wood, glass mat/gypsum sheathing, masonry, concrete and metal.

Ideal for Vertical & Horizontal Surfaces

S.A.M. provides excellent adhesion properties during the application process, and is very effective on either horizontal or vertical surfaces. Actual drying time depends on the ambient temperature and humidity during application, but requires a minimum 30 minutes for flash off time.

Cleans and Dries Quickly

IKO S.A.M. Adhesive is a quick-drying, solvent-based surface preparation for use with IKO self-adhering roofing membranes or IKO AquaBarrier self-adhering membranes. All substrates should be clean, dry and free from dust, dirt, oil and grease. IKO S.A.M. Adhesive cleans up easily with mineral spirits.

Easy to Apply/Bulk Packaged

IKO S.A.M. Adhesive may be applied by using a brush, roller, or by mechanically spraying.

S.A.M. Adhesive

SELF-ADHERING
MEMBRANE ADHESIVE



COMMERCIAL



IKO S.A.M. Adhesive should always be used in well-ventilated conditions and kept away from all sources of potential ignition.

All local health and safety rules and precautions should be followed when working with IKO products.

Good building practices include ensuring the application surface is adequately prepared for adhesion of the product prior to installation. For further details, please refer to the "IKO Installation Guidelines."

Please contact your *IKO Technical Representative* for specific slope requirements.

CHARACTERISTICS	UNITS	NOMINAL VALUE
Specific Gravity	Kg/L	0.80
Percent Solids	% wt./wt.	35
Viscosity @ 25°C	cps	200 - 400
Coverage (Approximate):	m ² /L (ft ² /gal)	3 to 6 (122 to 244)
Minimum Application Temperature	°C (°F)	-10 to 40 (14 to 104)
Service Temperature	°C (°F)	-40 to 66 (-40 to 150)

See also Material Safety Data Sheet MSDS #1147. The information on this product information sheet is based upon data considered to be true and accurate, based on laboratory tests and production measurements, and is offered solely for the user's consideration, investigation and verification. Nothing contained herein is representative of a warranty or guarantee for which the manufacturer can be held legally responsible. The manufacturer does not assume any responsibility for any misrepresentation or assumptions the reader may formulate.

